Fire resistant safety glass for interior application

CLASSIFICATION

PRODUCT FEATURES

EW = Inte

= Integrity + Radiation reduction

Ability to withstand fire exposure without transmission of fire to the non-fire side as a result of the passage of flames or hot gases, thereby causing ignition of the non-fire exposed surface or materials adjacent.


Also maintains radiated heat in front of the glazing below a specified level to provide for safer separation distances and escape ways.

Fire resistant safety glass in a toughened safety glass make-up

Edge Sealant

Intumescent material***

Silicone Sealant***



TECHNICAL SPECIFICATIONS

Fire resistance (EN 13501-2)	EW 60
Reaction to fire (EN 13501-1)	A2-s1, d0
Production height (Standard/Maximum)	≤ 3210 mm/≤ 3800 mm
Maximum Glass Size	Variable, subject to glass make-up, framing material or glazed element type. Refer to applicable fire
	test evidence, national certification and EXAP allowance. Consult with your Vetrotech representative.
Thickness tolerance	+2/-1 mm
Length tolerance	±2 mm
Impact resistance (EN 12600)	1 (B) 1 classification
UV stability (EN ISO 12543-4 point 6)	In addition to the standard specifications: no formation of bubbles or yellowing after
	2000 hours of exposure to radiation.
Edge quality outer pane	Polished edge in conformance with EN 12150-1
Application Conditions	Avoid prolonged exposure to extreme temperatures. Exterior applications must be supplied
	as an IGU with Low-E or Solar Control coating. For more information consult your Vetrotech
	representative or refer to "Quality Guideline, Application Conditions".
CE certificate No. of conformity	0336-CPD-5064C/ID No.* (you can obtain a DoP** from your national sales office) - AoC-level 1
Hazardous material contained	None
Assembly	According to the instruction guideline

Nominal thickness 20 mm

Glass size per thickness	≤ 2300 x 3800 mm
Weight (max. 500 kg/pane)	46 kg/m ²
Sound reduction Rw (EN 140-3)	39 dB
Light transmission (EN 410)	84%
Light reflection ρL (outside/inside)	8%/8%
U value, W/m ² K (EN 673)	4,9
g value	0,68
Energy transmission τΕ	61%
Energy reflection ρE (outside/inside)	7%/7%



Where progress never stops

Tel: 003293955599 Fax: 003293955099 info@newglasstech.com http://newglasstech.com



^{*} ID No. = Identification number for the relevant manufacturing site

^{**} Declaration of Performances