

CONTRAFLAM[®] 30 CONTOUR

Bent Fire resistant safety glass for interior application

CLASSIFICATION

EI = Integrity +
Insulation


Ability to withstand fire exposure without transmission of fire to the non-fire side as a result of the passage of flames, hot gases or significant conduction of heat, thereby causing ignition of the non-fire exposed surface or materials in contact, and provides a barrier to heat to protect people.

PRODUCT FEATURES

Toughened safety glass

Intumescent Interlayer

Edge Sealant



TECHNICAL SPECIFICATIONS

Fire resistance (EN 13501-2)

Reaction to fire (EN 13501-1)

Maximum Glass Size

Thickness tolerance

Length tolerance

UV stability (EN ISO 12543-4 point 6)

Application Conditions

CE certificate No. of conformity

Hazardous material contained

EI 30

A2-s1, d0

Variable, subject to glass make-up, framing material or glazed element type.

Consult with your Vetrotech representative.

+3/-2 mm

±2 mm

In addition to the standard specifications: no formation of bubbles or yellowing after 2000 hours of exposure to radiation.

Avoid prolonged exposure to extreme temperatures. Exterior applications must be supplied as an IGU with Low-E or Solar Control coating. For more information consult your Vetrotech representative or refer to "Quality Guideline, Application Conditions".

0336-CPD-5064C/ID No.* (you can obtain a DoP** from your national sales office) - AoC-level 1

None

Nominal thickness

Glass size per thickness

Weight

Sound reduction R_w (EN 140-3)

Light transmission (EN 410)

Light reflection ρ_L (outside/inside)

U value, W/m^2K (EN 673)

g value

Energy transmission τ_E

Energy reflection ρ_E (outside/inside)

18 mm

≤ 922 mm x 1890 mm

39 kg/m²

40 dB

85%

9%/9%

4,8

0,70

63%

7%/7%

* ID No. = Identification number for the relevant manufacturing site

** Declaration of Performances